Interior sealing primer

内墙封闭底漆

Source: BETC-HJ-2024-D-00259 | 2024-05-27

Basis: GB 18582-2008

Results for the submitted interior sealing primer only; not transferable to exterior primers, wall consolidants or floor consolidants.

仅对应内墙封闭底漆送检样品，不代用于外墙底漆、墙固或地固。

Property / 检测项目	Unit	Source criterion	Recorded result
Volatile organic compounds (VOC) 挥发性有机化合物 Detection limit: 2 g/L	g/L	≤120	13
Sum of benzene, toluene, ethylbenzene and xylenes 苯、甲苯、乙苯、二甲苯总和 Detection limit for sum: 50 mg/kg	mg/kg	≤300	Not detected
Free formaldehyde 游离甲醛 Detection limit: 5 mg/kg	mg/kg	≤100	12
Soluble lead (Pb) 可溶性铅 Detection limit: 2.97 mg/kg	mg/kg	≤90	Not detected
Soluble cadmium (Cd) 可溶性镉 Detection limit: 0.13 mg/kg	mg/kg	≤75	Not detected
Soluble chromium (Cr) 可溶性铬 Detection limit: 0.77 mg/kg	mg/kg	≤60	Not detected
Soluble mercury (Hg) 可溶性汞 Detection limit: 0.05 mg/kg	mg/kg	≤60	Not detected

Read the complete original source alongside this transcription. Results apply to the submitted specimen; archive dates and standard editions are retained. This sheet is not a new laboratory certificate.