Liquid marble multicolor coating

水包水多彩液态理石漆

Source: Printed handbook · KY-1040 | Archive supplied 2026

Basis: Methods as printed in the manufacturer brochure

Reformatted manufacturer brochure data, not an independent laboratory report. Refer to the original handbook page and exact product model.

厂家画册逐项数据的重新排版，不是第三方检测报告。以原画册页和具体型号为准。

Property / 检测项目	Unit	Source criterion	Recorded result
Condition in container GB/T 9755		Normal	Normal
Storage stability GB/T 9755 / GB/T 9268		Pass / No change	Pass / No change
Surface-dry time GB/T 1728		≤4 h	<4 h
Alkali resistance GB/T 9265 / ASTM D-1308		48 h; No abnormality	No abnormality
Water resistance GB/T 1733		96 h; No abnormality	No abnormality
Scrub resistance GB/T 9266 / ASTM D-2486		≥2000 cycles	>2000 cycles
Acid-rain resistance —		48 h; No abnormality	No abnormality
Temperature cycling JG/T 25 / ASTM E-2485		5 cycles; No abnormality	No abnormality
Dirt pick-up resistance GB/T 9780		≤2 Grade	1 Grade
Artificial weathering GB/T 1865		1000 h; No blistering, peeling or cracking	Pass; No chalking, obvious colour or gloss change

Read the complete original source alongside this transcription. Results apply to the submitted specimen; archive dates and standard editions are retained. This sheet is not a new laboratory certificate.

Original PDF page 14 · 00-纸质版1-10.pdf