Alkali-resistant sealer / anti-fungal exterior primer

抗碱封闭底漆 / 防霉抗藻外墙底漆

Source: Printed handbook · KY-1060 | Archive supplied 2026

Basis: Methods as printed in the manufacturer brochure

Reformatted manufacturer brochure data, not an independent laboratory report. Refer to the original handbook page and exact product model.

厂家画册逐项数据的重新排版，不是第三方检测报告。以原画册页和具体型号为准。

Property / 检测项目	Unit	Source criterion	Recorded result
Fungal resistance (anti-fungal variant) GB/T 1741-2007; 28 d		—	0 Grade
Condition in container JG/T 210		No lumps; uniform	Pass
Application workability JG/T 210		No application difficulty	No application difficulty
Low-temperature stability GB/T 9268		No change	No change
Surface-dry time GB/T 1728		≤2 h	<2 h
Water resistance GB/T 1733		96 h; No abnormality	No abnormality
Alkali resistance GB/T 9265 / ASTM D-1308		48 h; No abnormality	No abnormality
Water permeability JG/T 210		≤0.3 mL	0.3 mL
Efflorescence resistance JG/T 210		120 h; No abnormality	No abnormality
Compatibility with subsequent coats JG/T 210		Normal	Normal

Read the complete original source alongside this transcription. Results apply to the submitted specimen; archive dates and standard editions are retained. This sheet is not a new laboratory certificate.

Original PDF page 62 · 00-纸质版1-10.pdf