Natural stone / rock-chip coating

天然真石漆 / 岩片漆

Source: Printed handbook · KY-1070 | Archive supplied 2026

Basis: Methods as printed in the manufacturer brochure

Reformatted manufacturer brochure data, not an independent laboratory report. Refer to the original handbook page and exact product model.

厂家画册逐项数据的重新排版，不是第三方检测报告。以原画册页和具体型号为准。

Property / 检测项目	Unit	Source criterion	Recorded result
Condition in container JG/T 24		No lumps; uniform	Pass
Initial drying crack resistance JG/T 24		No cracking	No cracking
Bond strength JG/T 24 / ASTM C-297		≥0.7 MPa (102 psi)	0.9 MPa
Water resistance GB/T 1733		96 h; No abnormality	No abnormality
Alkali resistance JG/T 24		96 h; No abnormality	No abnormality
Artificial weathering GB/T 1865 / ASTM G-154		≥600 h; No abnormality	600 h; No abnormality
Reaction to fire (optional inorganic variant) GB 8624 / ASTM E-84		Class A	Pass

Read the complete original source alongside this transcription. Results apply to the submitted specimen; archive dates and standard editions are retained. This sheet is not a new laboratory certificate.

Original PDF page 26 · 00-纸质版1-10.pdf