Art-texture coating

艺术质感涂料

Source: Printed handbook · KY-1080 | Archive supplied 2026

Basis: Methods as printed in the manufacturer brochure

Reformatted manufacturer brochure data, not an independent laboratory report. Refer to the original handbook page and exact product model.

厂家画册逐项数据的重新排版，不是第三方检测报告。以原画册页和具体型号为准。

Property / 检测项目	Unit	Source criterion	Recorded result
Initial drying crack resistance JG/T 24		No cracking	No cracking
Bond strength JG/T 24 / ASTM C-297		≥0.7 MPa	0.9 MPa
Water resistance GB/T 1733		96 h; No abnormality	No abnormality
Artificial weathering GB/T 1865 / ASTM G-154		≥600 h	600 h; No abnormality
VOC GB 18582-2020 / US EPA 24		—	<50 g/L

Read the complete original source alongside this transcription. Results apply to the submitted specimen; archive dates and standard editions are retained. This sheet is not a new laboratory certificate.

Original PDF page 32 · 00-纸质版1-10.pdf