Water-based fluorocarbon metallic coating

水性氟碳金属漆

Source: Printed handbook · KY-1090 | Archive supplied 2026

Basis: Methods as printed in the manufacturer brochure

Reformatted manufacturer brochure data, not an independent laboratory report. Refer to the original handbook page and exact product model.

厂家画册逐项数据的重新排版，不是第三方检测报告。以原画册页和具体型号为准。

Property / 检测项目	Unit	Source criterion	Recorded result
Artificial weathering GB/T 1865 / ASTM G-154		≥1000 h; No abnormality	1000 h; No abnormality
Gloss retention GB/T 1865		≥80%	≥85%
Dirt pick-up resistance GB/T 9780		≤10%	5%
Adhesion GB/T 9286 / ASTM D-3359		≥1 Grade / ≥4B	1 Grade / 5B
Water / alkali resistance GB/T 1733 / 9265		96 h / 48 h; No abnormality	No abnormality
VOC GB 18582-2020 / US EPA 24		—	<50 g/L

Read the complete original source alongside this transcription. Results apply to the submitted specimen; archive dates and standard editions are retained. This sheet is not a new laboratory certificate.

Original PDF page 38 · 00-纸质版1-10.pdf