

Exterior Latex Paint

A smooth exterior wall finish for building facades and renovation specifications.

A compiled product summary, not a formally issued TDS, SDS or certification.

When to use this

Exterior walls. Discuss the substrate condition, color and compatible primer.

Technical data

Property	Value	Test method / conditions	Document basis
Surface-dry time	1 h	GB/T 9755-2014	BETC-HJ-2024-P-00256 / 2024-05-26
Contrast ratio (white and light colours)	0.92	GB/T 9755-2014	BETC-HJ-2024-P-00256 / 2024-05-26
Dirt pick-up resistance (white and light colours)	8 %	GB/T 9755-2014	BETC-HJ-2024-P-00256 / 2024-05-26
Scrub resistance	No damage after 2000 cycles	GB/T 9755-2014	BETC-HJ-2024-P-00256 / 2024-05-26
Alkali resistance	No abnormality after 48 h	GB/T 9755-2014	BETC-HJ-2024-P-00256 / 2024-05-26
Water resistance	No abnormality after 96 h	GB/T 9755-2014	BETC-HJ-2024-P-00256 / 2024-05-26
Water permeability	0.8 mL	GB/T 9755-2014	BETC-HJ-2024-P-00256 / 2024-05-26
Artificial weathering	400 h; no blistering, peeling or cracking; chalking 0, colour change 0	GB/T 9755-2014	BETC-HJ-2024-P-00256 / 2024-05-26

Application & system

Property	Value	Test method / conditions	Document basis
Theoretical coverage / consumption	Approximately 11 m²/L/coat	Source document	Manual V3 2026-07-09
Recommended coats	2 coats	Source document	Manual V3 2026-07-09
Application method	Roller or airless spray	Source document	Manual V3 2026-07-09
Application temperature	5–35 °C	Source document	Manual V3 2026-07-09
Relative humidity	≤85 %	Source document	Manual V3 2026-07-09

Recoat / clear-coat interval	≥4 h at 25°C	Source document	Manual V3 2026-07-09
------------------------------	--------------	-----------------	----------------------

Source and scope

Original reports may show the manufacturer's other brand name. The company confirms that the corresponding ARCHORA products use the same formulation and specifications.

Manufacturer's manual data is not an independent test report. Reported results apply to the submitted sample and stated test conditions; they do not establish performance on every job site or constitute international certification.

--	--	--

--	--	--